

09/300,544

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Quinn et al

Examiner: P. Mulcahy

Serial #: 09/300,544

Group Art Unit: 1713

Filed: April 27, 1999

Docket: EI-084-US-02

Title: **IMPROVED HOT MELTS UTILIZING A HIGH GLASS TRANSITION  
TEMPERATURE SUBSTANTITALLY SATURATED ALIPHATIC  
TACKIFYING RESIN**

Patent

**Official****FAX RECEIVED**

JAN 22 2001

**GROUP 1700**Freek  
9/c

(C)

1/31/01

AMENDMENT UNDER Rule 116

Assistant Commissioner for Patents  
Washington D.C. 20231

Dear Sir:

This is in response to the Final Office Action of October 24, 2000. Examination  
and reconsideration is respectfully requested.

IN THE CLAIMS

Please amend the following Claims:

- 5-2  
K  
AT
1. (twice amended) A[n improved] hot melt adhesive composition[,] comprising:
- a) about 10% by weight to about 50% by weight of at least one substantially aliphatic tackifying resin having a glass transition temperature of greater than 65 [ 80] °C; [and]
  - b) about 20% to about 60% by weight of at least one thermoplastic polymer;
  - c) 0% by weight to about 40% by weight of at least one wax;
  - d) wherein said total tackifying resin concentration having a glass transition temperature of greater than 65 °C is less than said total polymer concentration.